

Flat Wire

Chemical composition

NBR 6006:1994

	%C	%Mn	%P (máx)	%S (máx)
1020	0.17/0.23	0.30/0.60	0.04	0.05
1022	0.17/0.23	0.70/1.00	0.04	0.05
1025	0.22/0.28	0.30/0.60	0.04	0.05
1030	0.27/0.34	0.60/0.90	0.04	0.05
1035	0.31/0.38	0.60/0.90	0.04	0.05
1040	0.36/0.44	0.60/0.90	0.04	0.05
1045	0.42/0.50	0.60/0.90	0.04	0.05
1050	0.47/0.55	0.60/0.90	0.04	0.05
1055	0.52/0.60	0.60/0.90	0.04	0.05
1060	0.55/0.66	0.60/0.90	0.04	0.05
1070	0.65/0.76	0.60/0.90	0.04	0.05
1075	0.70/0.80	0.50/0.80	0.04	0.05
1080	0.74/0.88	0.60/0.90	0.04	0.05
1085	0.80/0.94	0.70/1.00	0.04	0.05
1090	0.84/0.98	0.60/0.90	0.04	0.05
1095	0.90/1.04	0.30/0.50	0.04	0.05



**Our steel
goes into your
product.**

Armco do Brasil S.A.
Rua Zacarias Alves de Melo, 180
São Paulo - Brazil - 03153-110
Tel.: (55) (11) 6343-2600
Fax: (55) (11) 6343-2838
e-mail: armco@armco.com.br
www.armco.com.br